

PRODUCT DATA SHEET

SikaGrout® GP

GENERAL PURPOSE, PUMPABLE, SHRINKAGE-COMPENSATED CEMENTITIOUS GROUT

DESCRIPTION

SikaGrout® GP is a pumpable, shrinkage-compensated, flowable cementitious grout with extended working time to suit local ambient temperatures.

USES

SikaGrout® GP is a general purpose grout suitable for the following applications:

- Grouting works for machine foundations, anchor bolts, bridge bearings, etc.
- Filling of cavities, gaps, recesses, etc.
- Concrete repairs (pre-packed grouting)

CHARACTERISTICS / ADVANTAGES

- Easy to mix and apply
- Flowable consistency
- Rapid strength development
- Non-corrosive
- Non-toxic
- Iron and chloride free
- Shrinkage-compensated
- Good pumping properties

PRODUCT INFORMATION

Packaging	25 & 5 kg bag
Appearance / Colour	Grey premixed powder
Shelf life	Min. 6 months from the date of production if stored properly
Storage conditions	Store properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +10°C and +35°C. Protect from direct sunlight.

TECHNICAL INFORMATION

Compressive Strength	24 hours	15 – 20 N/mm ²	(ASTM C349 / C109)
	3 days	25 – 35 N/mm ²	
	7 days	30 – 38 N/mm ²	
	28 days	≥ 40 N/mm ²	
Expansion	≥ 0.1% at 3 hours		(ASTM C940)

APPLICATION INFORMATION

Mixing ratio	W/P = 13 – 15% (depending on the required consistency).
Yield	1 bag (25 kg) yields approx. 13.10 litres of mortar.

Approx. 76 bags (25 kg/bag) required for 1 m³ of mortar.

Layer Thickness	Min. 10 mm	
Ambient Air Temperature	+10°C min. / +40°C max.	
Substrate Temperature	+10°C min. / +40°C max.	
Flowability	250 – 320 mm	(ASTM C230)
Initial Set Time	≥ 5 h	
Final Set Time	≤ 12 h	
Fresh mortar density	~2.2 kg/l (depending on consistency and temperature)	

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATION

At temperatures +20°C and below, setting time and strength development will be slower.
Non-shrink grout contains additives which expand either during the plastic stage and / or the hardening stage to compensate for the shrinkage of the cementitious matrix. However, this 'non-shrink' property will be effective only if the material is not subjected to water loss. This is confirmed by ASTM C1107 Standard Specification for packaged dry, hydraulic cement grout (non-shrinkable).

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The substrate should be prepared by suitable mechanical preparation techniques such as high pressure water, breakers, grit blasting, scabblers, etc.

All absorbent surfaces must be well saturated with clean water, but free of any surface water or puddles prior to the application of SikaGrout® GP.

Concrete, mortar and stone

Surfaces must be sound, clean, free from frost, oils, grease, standing water and all loosely adhering particles and other surface contaminants.

Metal surfaces (iron and steel)

Surfaces should be clean, free from scale, rust, oil and grease.

MIXING

Place about 70–80 % of the premeasured clean water (depending on consistency required – refer to "Mixing Ratio") into a clean container and gradually add the whole bag of SikaGrout® GP into it while continuously mixing. Add the remaining water until the desired consistency is obtained.

Mix for 2–3 minutes with a low speed drill (500 rpm max.).

APPLICATION

After mixing, stir lightly with a spatula for a few seconds to release any entrapped air. The grout is then poured immediately into the prepared formwork. When carrying out baseplate grouting, ensure sufficient pressure head is maintained for uninterrupted mortar flow. The prepared formwork must be firmly in place and kept watertight.

When placing grout over a large area, it is important to maintain a continuous flow throughout. Work sequence must be properly organised to ensure an uninterrupted flow. In large areas, SikaGrout® GP may be pumped using heavy duty diaphragm pumps. Screw feed and piston pumps may also be used.

Grouting large volumes

For sections thicker than 60 mm, it is necessary to fill SikaGrout® GP with graded 10 mm silt-free aggregates to minimise temperature rise generated during the curing stage. The quantity of aggregates should not exceed 1 part aggregates to 1 part SikaGrout® GP by weight. For such mixes, a conventional concrete mixer and pump may be used. To further ensure that air entrapped during mixing is allowed to fully escape, it may be necessary to make breather holes. Use steel rods or chains to assist the flow of grout where necessary. Preliminary trials are recommended.

CURING TREATMENT

When using formwork, leave the formwork in place for at least 3 days.

Upon removal of the formwork, cure the exposed surfaces immediately with Antisol® curing compound or use other approved curing methods.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened material can only be mechanically removed.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users can always refer to the most recent version of the local Product Data Sheet for the relevant product, available on our website. The information in any downloaded version is valid as of the time of download.

Sika Limited (Vietnam)

Nhon Trach 1 Industrial Zone,
Nhon Trach Dist., Dong Nai Province,
Vietnam
Tel: (84-251) 3560 700
Fax: (84-251) 3560 699
sikavietnam@vn.sika.com



Product Data Sheet

SikaGrout® GP
August 2025, Version 01.02
020201010010000085

SikaGroutGP-en-VN-(08-2025)-1-2.pdf